

# **Fast Cure Thixotropic Epoxy Adhesives**

10-3005 NS - 5 MINUTE SET NON-SAG EPOXY 10-3020 NS - 20 MINUTE SET NON-SAG EPOXY 10-3046 NS - 46 MINUTE SET NON-SAG EPOXY

# **DESCRIPTION:**

These high bond strength adhesives are clear 100% solids, two component, non-sag adhesives with a quick setting time of 5-46 minutes at room temperature. They are excellent for bonding plated metals, pewter, glass, wood, ceramic, felt, cement, gem stones, most plastics and rubbers, etc...

These adhesives were tested in our laboratory for flame retardancy properties. According to our test results they meet the requirements of UL94HB.

# **APPLICATIONS:**

These unique adhesives are ideally suited for a wide range of electronic, electrical, industrial, structural, and jewelry applications. These adhesives are also an excellent choice for field repairs. They are offered in the popular TriggerBond® dual barrel cartridge dispensing system and bulk packaging.

## **FEATURES:**

- Non-sag consistency
- High bond strength
- Fast room temperature cure three speeds to choose from
- Water & chemical resistance
- Outstanding thermal shock resistance
- 1:1 mix ratio
- Impact resistance

# **TYPICAL SPECIFICATIONS (10-3005NS)**

111 IOAL 01 LOII IOATIONO (10-0003NO)	
Color	Semi-transparent (available in black)
Mix ratio by volume	1:1
Mixed viscosity, 25°C cps*	Non-Sag
Solids content, %	100
Specific gravity, 25°C	1.15
Shore D hardness	
10-3005NS	86
10-3020NS	72
10-3046NS	65
Work Life, 25°C, minutes	
10-3005NS	3-5
10-3020NS	10-15
10-3046NS	25-30
Handling time, 25°C, minutes	
10-3005NS	15-20
10-3020NS	30-35
10-3046NS	55-60
Cure time, 25 °C, hours	24-48

epoxies.com

21 Starline Way Cranston, RI 02921 USA



Coefficient of thermal expansion	00.40-6
(in/in/℃)	60x10 <sup>-6</sup>
Operating temperature range, ℃	<sup>-</sup> 50 to <sup>+</sup> 130
Dielectric strength,V/mil	420
Izod Impact ft-lb/in	2.7
Dielectric constant, 1KHz at 25°C	4.00
Dissipation factor, 1KHz at 25°C	.017
Volume resistivity, ohm-cm at 25°C	$2.0 \times 10^{14}$
Shear strength, psi	
Aluminum (etched)	1,500
Cold rolled steel	1,000
Copper	960
Brass	725
Stainless Steel	750
Galvanized Steel	900
ABS	500
PVC	335
Polycarbonate	250
Compression strength, psi	8,500
Coverage, .005 in. thick bond line,	
sq. ft./gallon	320

<sup>\*</sup> Also available in lower viscosity versions (10-3005, 10-3020, 10-3046).

# **INSTRUCTIONS FOR USE:**

- 1. Thoroughly mix equal parts of resin to catalyst by weight or volume.
- 2. Apply evenly to both surface(s) to be bonded.
- 3. Application to the substrates should be made within five minutes. Larger quantities and/or higher temperatures will reduce the working time. Avoid mixing large quantities and/or at high temperature due to the possibility of creating a high exothermic temperature.
- 4. Join the coated surfaces. Allow to cure at 60°F (16°C) or higher until adhesive is set. Heat may be added up to 200°F (93°C) to accelerate the cure.
- 5. Avoid moving parts during cure. Pressure to the substrates is recommended. Maximum shear strength is obtained with a 3-5 mil bond line.

### PREPARATION OF SURFACES:

Surfaces to be bonded must be clean and grease free. Adhesion can be substantially increased by abrading the surface with emery cloth, sand paper, etc... A roughened porous surface will produce the best results. Any oxidized metal films should be removed just prior to application of the adhesives.

#### **AVAILABILITY:**

Available in the TriggerBond® 50ml, 75ml, 200ml and 400ml dual barrel cartridges. Also packaged in quarts, gallons, and 5 gallon pails.

# **IMPORTANT:**

**EPOXIES, ETC. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE WITH RESPECT TO ITS PRODUCTS.** The information in this brochure is based on data obtained by our own research and is considered reliable. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from the use thereof, or that any such use will not infringe any patent. The properties given are typical values and are not intended for use in preparing specifications. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular purpose.

10/13 epoxies.com